

Revision: March 15, 2025 Supersedes: June 1, 2024 Ref. #: 511088

Paintable Silicone Supreme Kitchen & Bath Sealant

DESCRIPTION

GE Paintable Silicone Supreme Kitchen & Bath is a premium sealant with a hybrid formulation that combines the outstanding waterproof performance you would expect from a silicone sealant with the ease of use and paintability of an acrylic latex. This sealant is ideal for kitchen and bath projects and interior applications and can be exposed to water or be painted in as little as 60 minutes. Paintable Silicone Supreme sealant is low odor, offers 10-year mold-free product protection, can withstand scrubbing, and has long-lasting durability. This sealant is permanently flexible and will not break down, crack, or crumble over time and is backed by a lifetime guarantee.

Available as:

Item #	Country	Package	Size	Color
2733743	USA	Plastic cartridge	9.5 fl. oz. (280 mL)	White

FEATURES & BENEFITS

- Hybrid performance and paintable
- 30-minute water-ready [1]
- 60-minute paint-ready [2]
- Resists mold [3] with 10-year mold-free product protection
- Permanent flexibility

- Excellent adhesion to wet or dry surfaces [4]
- · Shrink & crack-proof
- · Low odor
- Meets ASTM C-920 Class 50 specifications
- Lifetime Guarantee

RECOMMENDED FOR

Paintable Silicone Supreme Kitchen & Bath sealant is designed for use in a wide variety of applications including but not limited to walls, backsplashes, countertops, around fixtures, tubs, tile, and plumbing. It can be used on common kitchen and bath materials including most metals, plastics and wood, glass, drywall, plaster, granite, cultured marble, ceramic and porcelain tile, natural stone, cement board, HP laminate, fiberglass, aluminum, and painted surfaces.

LIMITATIONS

Should not be considered:

- For structural repairs
- For use underwater or in other applications where the product will be in continuous contact with water
- For use in food contact applications (direct or indirect)
- For use in aquariums

- · On frozen or contaminated surfaces
- On excessively basic or acidic substrates
- For use on surfaces that are above 140°F (60°C)
- For use under shower door tracks, or as a spackling compound.
- For use on surfaces with special coatings, such as mirrors, without approval of the article's manufacturer

COVERAGE

For a 9.5 fl. oz. (280 ml) cartridge:

- A 1/4" (6 mm) bead extrudes approx. 29.1 ft. (8.9 m)
- A 3/8" (9.5 mm) bead extrudes approx. 13.3 ft. (4 m)



Revision: March 15, 2025 Supersedes: June 1, 2024 Ref. #: 511088

TECHNICAL DATA

Typical Uncured Physical Properties			Typical Application Properties			
Color: Appearance:	White Non-slumping paste Silane Modified Polymer Alcohol		Application Temperature: (substrate & ambient)	Can be applied between 0°F (-18°C) and 140°F (60°C). Sealant should be above 41°F (5°C) and below 104°F (40°C)		
Base:						
Odor:				For best results, apply between 60°F (16°C) – 100°F (38°C)		
VOC Content:	2.9% by weight	CARB	Skin Formation Time:	15 – 20 minutes*		
	34.8 g/L	SCAQMD	Tack Free Time:	15 hours	ASTM C679	
Shelf Life:	24 months from date of manufacture (unopened)		Cure Time:	24 – 72 hours*		
			Cure Rate:	~2 – 3 mm/ 24 hours*		
Lot Code Explanation: YYDDD YY = Last two digits of year of manufacture DDD = Day of manufacture based on 365 days in a year Example: 22076 = March 17, 2022 is the manufacture date			Clean Up:	Clean up uncured adhesive residue with mineral spirits. Cut or scrape away cured adhesive using a sharpedged tool. Note this may result in damage to surfaces. Follow solvent manufacturer's precautions for using solvents.		

^{*} At 73°F (23°C) and 50% relative humidity using 1/4" (6mm) thick bead
Time is dependent on temperature, humidity, porosity of substrate, and thickness of bead applied. Cure time is significantly increased in cold temperatures and/or low humidity conditions.

Typical Cured Performance Properties								
Color:	White	Service Temperature:	-14°F (-25°C) to 158°F (70°C)					
Cured form:	Non-flammable, rubbery solid	Shore A Hardness:	32	ASTM C661				
Water Resistant:	Yes, 30-minute water ready [1]	Joint Movement Capability:	± 50%	ASTM C719				
Paintable:	Yes, with latex paint or primer [2]	Tensile Strength:	234 psi	ASTM D412				
Shrinkage:	Nil	Elongation at Break:	577%	ASTM D412				
Specifications:	ASTM C-920, Type S, Grade NS, Use NT, Class 50, M, G, and A							

^[1] Exposure to rain or water possible in as little as 30 minutes with bead size max 1/4" (4.8 mm), temperature min 65°F (18.3°C) and humidity min 50%. Otherwise, sealant should not be exposed to water for 8 hours. Do not touch or clean caulk for 24 hours.

^[2] Sealant can be painted 60 minutes after application with latex paint or primer for bead size 1/4", temperature min 65°F & humidity min 50%. Otherwise, sealant should not be painted for 2 hours. Allow to dry 24 hours if using oil-based paints, using latex primer first and test on an inconspicuous area for best results. Apply paint with reduced applicator pressure to avoid disturbing the caulk. Clean-up with a damp, disposable cloth; do not rinse.

^[3] Fully cured sealant is resistant to stain-causing mold & mildew. Regular cleaning of sealant is required, however, as soap and other residues including airborne spores, pollen and other organic contaminates can cause secondary mold and mildew growth.

^[4] Sealant can be applied to damp or dry surfaces. For wet surfaces, wipe off excess water before applying. Do not apply to materials that are water saturated such as wood and concrete. Do not use in areas of ponding water.



Revision: March 15, 2025 Supersedes: June 1, 2024 Ref. #: 511088

DIRECTIONS

Tools Typically Required:

Utility knife, caulking gun, and tool to puncture cartridge seal.

Safety Precautions:

Wear gloves and wash hands after use.

Surface Preparation:

- Surfaces must be clean, dry, and sound prior to application of the sealant. All contaminants, impurities, or other adhesion inhibitors (such as frost, oils, old sealants, soaps, and other surface treatments, etc.) must be removed from the surfaces to which the sealant is intended to adhere to. Cleaning of surfaces should be done within 1 to 2 hours before sealant is to be applied, to allow surfaces to dry.
- For cleaning a solvent-dampened, clean rag usually produces the desired result. Isopropyl alcohol (IPA) is a commonly used solvent that has shown to be effective with most non-porous substrates. When handling solvents, refer to manufacturer's SDS for information on handling, safety, and personal protective equipment.
- Use backer rod for gaps deeper than 3/8" (9.5 mm). A width to depth ratio of 2:1 should be maintained.
- Architectural coatings, paints, and plastics should be cleaned with a solvent approved by the manufacturer of the product, or which does not harm or alter the finish.
- Since porous materials can absorb and retain moisture, it is important to confirm that substrates are dry prior to application
 of the sealant.

<u>Masking:</u> The use of masking tape is recommended, where appropriate, to ensure a neat job and to protect adjoining surfaces from over-application of sealant. Masking tape should be removed immediately after tooling the sealant and before the sealant begins to skin over (tooling time).

Application:

- Cut nozzle to obtain desired bead size and pierce inner foil seal.
- Using a caulking gun, apply sealant in a continuous operation applying a positive pressure adequate to properly fill and seal the seam, cavity, or joint.
- Smooth or tool the sealant into gap within 15 minutes of application. Tool or strike the sealant with a concave tool, applying light pressure to spread the material against the joint surfaces to ensure a void-free application.
- When tooling, use care not to spread the sealant over the face of the substrates adjacent to the joint or masking as Paintable Silicone Supreme Kitchen & Bath sealant can be extremely difficult to remove from rough or porous substrates. Excess sealant should be cleaned from glass, metal, and plastic surfaces while still uncured. On porous surfaces the excess sealant should be allowed to progress through the initial cure or set-up. It should then be removed by abrasion or other mechanical means
- If sealant is applied when the temperature is below 40°F (4°C) or if frost or moisture is present on the surfaces to be sealed, the rate of cure will slow. For standard cure speed, apply when temperatures are above 40°F (4°C).
- The cure rate of this product is primarily dependent upon temperature and the availability of atmospheric moisture. Under average conditions (relative humidity of 50 ± 5% at an air temperature of 73.4 ± 2°F (23 ± 1°C)) this material can attain a cured thickness of 2-3 mm per 24 hours (assuming ample access to atmospheric moisture). As temperature decreases, the cure rate slows down (and vice versa). Low moisture environments will also reduce the cure rate. In near-confined spaces, which limit the overall access to atmospheric moisture, sealant will cure only from that surface which has access to the atmosphere.

NOTE:

- Some materials that bleed plasticizers or oils can cause a discoloration on the surface of sealants. When sealing to or over items such as: rubberized gaskets, bituminous based materials, butyl or oil-based products, oily woods, tapes, etc., compatibility testing prior to use is recommended.
- Silicone materials are hydrophobic in nature and if inadvertently over-applied onto adjacent joint surfaces (even if removed immediately), it can create a waterproofing effect of a substrate when the substrate is wet. See comment on Masking.
- While Paintable Silicone Supreme Kitchen & Bath Sealant is generally considered a non-priming sealant, special circumstances or substrates may require a primer. It is the user's responsibility to test substrate compatibility, and the adhesion of the cured sealant on a test joint before applying to the entire project.
- Customers must evaluate GE branded products and make their own determination as to fitness of use in their particular application.
- In addition to the guidelines provided on this datasheet, Henkel Corporation recommends that designers and users of Paintable Silicone Supreme sealant familiarize themselves with the latest editions of the following industry guidelines and best practices:
 - 1.) ASTM C1193 Standard Guide for Use of Joint Sealants.



Revision: March 15, 2025 Supersedes: June 1, 2024 Ref. #: 511088

STORAGE & DISPOSAL

NOT DAMAGED BY FREEZING. Store in unopened containers in a cool, dry area away from heat and direct sunshine under standard conditions. Standard storage conditions are defined as 72 ± 4°F (22 ± 2°C) and < 50% relative humidity. Elevated temperatures or extreme cold temperatures will reduce shelf life. In cool or cold weather, store container at room temperature for at least 24 hours before using. Use an approved hazardous waste facility for disposal facility. Hardened material may be

LABEL PRECAUTIONS

WARNING! UNCURED SEALANT IRRITATES EYES, SKIN AND RESPIRATORY TRACT.

WARNING! Contains phthalate esters and silanes. May be harmful if inhaled or swallowed. Methanol is released during application and cure, which may affect the nervous system causing dizziness, headache, or nausea. Use in a wellventilated area. Do not breathe vapors. Avoid eye and skin contact. Prolonged or repeated skin contact with uncured sealant may cause irritation. Wear gloves and safety glasses when applying product. Remove contact lenses before using sealant. Wash hands after using.

FIRST AID: For eye contact flush with water for 15 minutes. Call a physician if irritation develops and persists. For skin contact, wash thoroughly with soap and water. If affected by inhalation, remove to fresh air and get medical attention. If ingested, do not induce vomiting; call a physician or Poison Control Center immediately. DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.

WARNING: Cancer and Reproductive Harm – www.P65Warnings.ca.gov

Refer to the Safety Data Sheet (SDS) for further information

DISCLAIMER

The information and recommendations contained herein are based on our research and are believed to be accurate, but no warranty, express or implied, is made or should be inferred. Henkel recommends purchasers/users should test the products to determine acceptable quality and suitability for the intended use. All adhesive/sealant applications should be tested under simulated or actual end use conditions to ensure the adhesive/sealant meets or exceeds all required project specifications. Since assembly conditions may be critical to adhesive/sealant performance, it is also recommended that testing be performed on specimens assembled under simulated or actual production conditions. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement, or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

LIMITED WARRANTY

LIMITED LIFETIME GUARANTEE: Manufacturer warrants that this product, when used as directed, will meet the above specifications for as long as you own your home. If not satisfied, return proof of purchase for refund. This is the sole and exclusive remedy and Manufacturer shall not be liable for any damages in excess of the purchase price. THIS WARRANTY IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS. For warranty assistance, contact Henkel at 1.877.607.7407 M-F 9:00 am to 4:00 pm ET.

GE is a registered trademark of General Electric Company and is used under trademark license by Henkel.

For Technical Assistance call: 1-877-607-7407 - Mon - Fri 9:00a - 4:00p ET www.gesealants.com



Founded in 1876, Henkel is a global leader in the consumer and industrial businesses. Henkel operates worldwide with leading brands and technologies in three business areas: Laundry & Home Care, Beauty Care and Adhesive Technologies.

Henkel Corporation - Professional & Consumer Adhesives Headquarters - Rocky Hill, CT 06067 www.henkelna.com